

ABSTRACT OF THE DISCLOSURE

On a given substrate are successively formed electrode patterns constituting electrode wirings for measuring points, respectively. Then, an insulating layer and an underlayer covering the electrode patterns are etched and removed to expose the substrate, which suffers from anisotropic etching using a given etching solution, to fabricate a multipoint minute electrode with a sharpened probe and a supporter for the probe.